

UTP Fluxes

UTP Flux	Group DIN 8511	Groups DIN EN 1045 DIN EN 29 454	Effective temperature range °C	Applications	Availability 1/2 and 1/1 boxes
Fluxes for silver solders					
UTP Flux AGF-S	F-SH 1			Universal silver solder flux	Paste
UTP Flux AGX	(silver solders)	FH 10	500 – 800	Universal silver solder flux	Powder
UTP Flux 3 W				Universal silver solder flux	Powder
UTP Flux HF	F-SH 1	FH 12	650 – 1000	Silver solder flux for high-frequency induction soldering	Paste
Fluxes for brazing alloys					
UTP Flux HLP	F-SH 2			Universal brazing alloy flux	Powder
UTP Flux HLS	(brazing alloys)	FH 21	700 – 950	Universal brazing alloy flux	Paste
UTP Flux HLS-B				Special flux for brazing with UTP I/ UTP I MR	Paste
UTP Flux 4 Mg	F-LH 1 (aluminium)	FL 10	500 – 700	Universal flux for aluminium casting and forging alloys	Powder

* available on request

ЗАО «Ресурс»
Россия г.Новосибирск
ул. Объединения, 9.
т/ф (383) 363-26-24,
т/ф (383) 291-93-02
e-mail: resurszao@ya.ru

